

KIMIDUR® PBT(825GNV0)

MATERIAL NAME: PBT **COLOR:** NATURAL **CODE:** PBT825GNV0

MATERIAL DESCRIPTION: Kimiadur® PBT825GNV0 is a 25% glass fiber reinforced, flame retardant prime, natural Polybutylene terephthalate resin for injection molding.

No.	PROPERTIES		METHOD	UNIT	VALUE
PHYSICAL PROPERTIES					
1	ASH CONTENT		ISO 3451	%	31
2	RELATIVE DENSITY		ISO 1183	g/cm ³	1.65
3	VISCOSITY NUMBER		ISO 307	Cm ³ /gr	-
4	MOISTURE CONTENT		ISO 62	%	0.20
MECHANICAL PROPERTIES					
5	TENSILE STRENGTH AT BREAK (5mm/min)		ASTM/D638	MPa	113
6	ELONGATION AT BREAK (5mm/min)		ASTM/D638	%	8.5
7	TENSILE MODULUS (5mm/min)		ASTM/D638	MPa	8200
8	NOTCHED IMPACT STRENGTH-IZOD		ISO 180	Kj/m ²	8.3
9	UN NOTCHED IMPACT STRENGTH-IZOD		ISO 180	Kj/m ²	50.0
THERMAL PROPERTIES					
10	HARDNESS		ISO 868	Shore D	73
11	MFI		ASTM/D1238	g/10min	-
12	VICAT(50° C/h)	10N	ASTM/D1238	° C	-
		50N			-
FLAMMABILITY					
13	HDT (120° C/h)	264psi	ASTM/D648	° C	-
		66psi			-
14	Flammability	Class	UL94	-	V0
INJECTION PROCESS PARAMETERS					
<i>Loading</i>		<i>Injection</i>		<i>Degassing</i>	
<i>Speed</i>	<i>Pressure (Bar)</i>	<i>Speed</i>	<i>Pressure (Bar)</i>	<i>Temperature</i>	<i>Time</i>
60	80	60	80	80 °C	0.5h
<i>Mold Releasing</i>		<i>Zone</i>			
<i>Good</i>		5	4	3	2
		- °C	225 °C	230 °C	235 °C
					1
					240 °C